



## Obomodulan® Type 600 Technical Data

Identification #	600
Color	Mocca
Density lbs/ft <sup>2</sup>	37
Compressive strength psi	2560
Flexural strength psi	2760
Expansion coefficient range	30 x 10 <sup>-6</sup>
Shore D hardness	58
Max. working temp. deg. F	176

Metric actual mm • US approx. in.	600
50 x 500 x 1500mm • 2 x 20 x 60"	●
75 x 500 x 1500mm • 3 x 20 x 60"	●
100 x 500 x 1500mm • 4 x 20 x 60"	●
150 x 500 x 1500mm • 6 x 20 x 60"	●

Identification #	600
Applications	Master models

## Obomodulan® 600 Tooling Board

